

INDAG RETREADING



SALIENT FEATURES»

Super Strong Bonding

High stretchability

Rapid rate of bond formation

Maximum Green Tack

Uniform curing

No tread lifting

More mileage



URSG-UNVULCANISED RUBBER STRIP GUM

IN 30

ADVANTAGES:

- Strong Bonding Between Casing and Tread
- Cost Effective Retreading
- Protection Against Casing Failure
- Increases Casing Retreadability

TECHNICAL SPECIFICATIONS

- Curing Temperature: 99 -101 °C
- Curing Time: 220 Minutes

To be used for chamber only

IN 40

ADVANTAGES:

- Strong Bonding Between Casing and Tread
- Shorter Curing Time
- Designed Especially for Cooler Running

TECHNICAL SPECIFICATIONS

Chamber:

- Curing Temperature: 125 - 127 °C
- Curing Time: 150 Minutes

Bonder:

- Curing Pressure: 60 - 80 PSI
- Curing Time: 130 Minutes

Recommended for chamber

IN 50

ADVANTAGES:

- Shortest Curing Time
- High Retreading Productivity
- Sustains Good Bonding Strength at High Temperatures in Service

TECHNICAL SPECIFICATIONS

Chamber:

- Curing Temperature: 120 - 125 °C
- Curing Time: 120 Minutes

Bonder:

- Curing Pressure: 60 - 85 PSI
- Curing Time: 90 Minutes

Recommended for both chamber & bonder

